

Article

Preparation of Nanocomposite Plasmonic Films Made from Cellulose Nanocrystals or Mesoporous Silica Decorated with Unidirectionally Aligned Gold Nanorods

Michael G. Campbell ¹, Qingkun Liu ¹, Aric Sanders ², Julian S. Evans ¹ and Ivan I. Smalyukh ^{1,3,4,*}

¹ Department of Physics, University of Colorado, Boulder, CO 80309, USA;
E-Mails: michael.g.campbell@colorado.edu (M.G.C.); qingkun.liu@colorado.edu (Q.L);
julian.evans@colorado.edu (J.S.E.); Ivan.Smalyukh@colorado.edu (I.I.S.)

² National Institute of Standards and Technology, Boulder, CO 80305, USA;
E-Mail: aric.sanders@nist.gov

³ Department of Electrical, Computer, and Energy Engineering, Materials Science and Engineering Program, and Liquid Crystal Materials Research Center, University of Colorado, Boulder, CO 80309, USA

⁴ National Renewable Energy Laboratory, Renewable and Sustainable Energy Institute, University of Colorado, Boulder, CO 80309, USA

* Author to whom correspondence should be addressed; E-Mail: ivan.smalyukh@colorado.edu;
Tel.: +1-303-492-7277; Fax: +1-303-492-2998.

Received: 1 March 2014; in revised form: 24 March 2014 / Accepted: 26 March 2014 /

Published: 11 April 2014

Abstract: Using liquid crystalline self-

orientationally ordered anisotropic plasmonic nano-inclusions.

Keywords: gold nanorods; cellulose nanocrystals; liquid crystal; plasmonics; mesoporous silica

1. Introduction

Nanostructured materials are poised to revolutionize scientific instruments, technologies, and consumer devices. Liquid crystalline intermediate phases confer long-range orientational order that has been previously used to improve the properties of fibers and deposited films for biomedical [1], optical [2], and electronic [3,4] applications. Liquid crystals (LCs) can act as smart hosts that align anisotropic nanoparticle inclusions and leverage nanoscale anisotropy into device scale polarization sensitivity [5]. Self-assembly of plasmonic nanoparticles in LCs has been extensively studied recently [6–8]. Gold nanorods (GNRs) have two surface

Figure 3. SEM imaging of thin films of CNCs with embedded GNRs (with a thin carbon coat to improve conductivity). **(a,b)** Co-located images obtained with **(a)** in-lens (

polarization-dependent SPR effect, indicating that silica capped GNRs maintained their rod-like structure. Using low-voltage SEM, we observed that the films had a mesoporous structure, which was consistent with what was previously observed for such films without GNRs [21]. GNRs tended to be evenly dispersed throughout the film, with a lower degree of alignment than in the cellulose films. The estimated scalar order parameter of GNRs that we could achieve by polarization-dependent extinction spectra in this case was . The reduced value of the orientational order parameter may be partially due to the high-temperature treatment known to affect gold nanoparticles [22]. The longitudinal plasmonic peak shifted from 680 nm (Figure 1d, 2h) to 630 nm (Figure 3c) due to a combination of two effects, the nanorods being deformed by heating and the silica having different dielectric properties than the cellulose. However, it is interesting that the alignment persisted upon removal of CNCs, providing a potentially useful approach for scalable fabrication of composite mesostructured films with orientationally ordered plasmonic nanoparticles in a silica matrix. These obtained hybrid thin films can be practically useful. The mesoporous silica surface, which encloses the GNRs, can be functionalized with various chemicals, and the unique absorption properties of the film could be used to study chemical reactions, or to create a catalyst for chemical reactions. The presence of orientationally-ordered plasmonic nanostructures in such films may provide the means of efficient use of light for controlling and guiding reactions and processes in various applications.

Figure 4. Mesoporous silica films containing aligned GNRs. **(a,b)** Bright field polarizing microscopy images with the polarization parallel **(a)** and perpendicular **(b)** to the director. **(c)** Absorption spectra of the film as measured with polarization parallel (red) and perpendicular (blue) to the director. **(d,e)** TPL images of GNRs taken with polarization parallel **(d)** and perpendicular **(e)** to the director, confirming alignment of the gold nanoparticles with their long axes on-average parallel to the director. The homogeneous TPL signal in the images confirms uniform distribution of GNRs. **(f,g)** SEM images of the mesoporous film showing **(f)** alignment of GNRs and **(g)**

2.3. Discussion

Unlike their dichroic dye based counterparts, plasmonic polarizers allow for very precise control over the operational spectrum of a polarizer as well as the ability to polarize light of different wavelengths, including the ultraviolet and infrared parts of an optical spectrum [23]. The transverse plasmonic absorption is generally a function of the material used for the rod-like nanoparticles, with nickel having an absorption peak at 380 nm, silver absorbing at 420 nm, gold at 525 nm and copper at ~580 nm [23]. The longitudinal SPR

Materials

Materials

3. Xu, Z.; Gao, C. Graphene chiral liquid crystals and macroscopic assembled fibres. *Nat. Commun.* **2011**, *2*, 571.
4. Behabtu, N.; Young, C.C.; Tsentalovich, D.E.; Kleinerman, O.; Wang, X.; Anson, W.M.; Bengio, E.A.; Waarbeek, R.F.; Jong, J.J.; Hoogerwerf, R.E.; Fairchild, S.B.; Ferguson, J.B.; Maruyama, B.; Kono, J.; Talmon, Y.; Cohen, Y.; Otto, M.J.; Pasquali, M. Strong, light, multifunctional fibers of carbon nanotubes with ultrahigh conductivity. *Science* **2013**, *339*, 182–186.
5. Evans, J.S.; Beier, C.; Smalyukh, I.I. Alignment of high-aspect ratio colloidal gold nanoplatelets in nematic liquid crystals. *J. Appl. Phys.* **2011**, *110*, 033535.
6. Qi, H.; Hegmann, T. Formation of periodic stripe patterns in nematic liquid crystals doped with functionalized gold nanoparticles. *J. Mater. Chem.* **2006**, *16*, 4197.
- 7.

19. Uetani, K.; Yano, H. Semiquantitative structural analysis of highly anisotropic cellulose nanocolloids. *ACS Macro Lett.* **2012**, *1*, 651–655.
20. Smalyukh, I.I.; Zribi, O.V.; Butler, J.C.; Lavrentovich, O.D.; Wong, G.C.L. Structure and dynamics of liquid crystalline pattern formation in drying droplets of DNA. *Phys. Rev. Lett.* **2006**, *96*, 177801.
21. Shopsowitz, K.E.; Qi, H.; Hamad, W.Y.; MacLachlan, M.J. Free-standing mesoporous silica films with tunable chiral nematic structures. *Nature* **2010**, *468*, 422–425.
22. Petrova, H.; Juste, J.P.; Pastoriza-Santos, I.; Hartland, G.V.; Liz-Marzan, L.M.; Mulvaney, P. On the temperature stability of gold nanorods: comparison between thermal and ultrafast laser-induced heating. *Phys. Chem. Chem. Phys.* **2005**, *8*, 814–821.
23. Maier, S.A. *Plasmonics: Fundamentals and Applications*; Springer: Berlin, Germany, 2007.
24. Perez-Juste, J.; Liz-Marzan, L.M.; Carnie, S.; Chan, D.Y.C.; Mulvaney, P. Electric-field-directed growth of gold nanorods in aqueous surfactant solutions. *Adv. Funct. Mater.* **2004**, *14*, 571–579.
25. von Maltzahn, G.; Centrone, A.; Park, J.H.; Ramanathan, R.; Sailor, M.J.; Hatton, T.A.; Bhatia, S.N. SERS coded gold nanorods as a multifunctional platform for densely multiplexed near-infrared imaging and photothermal heating. *Adv. Mater.* **2009**, *21*, 3175–3180.
26. Fernandez-Lopez, C.; Mateo-Mateo, C.; Alvarez-Puebla, R.A.; Perez-Juste, J.; Pastoriza-Santos, I.; Liz-Marzan, L.M. Highly controlled silica capping of PEG-capped metal nanoparticles and preparation of SERS-encoded particles. *Langmuir* **2009**, *25*, 13894–13899.
27. Pawley, J. Low voltage scanning electron microscopy. *J. Microsc.* **1984**, *136*, 45–68.

© 2014 by the authors; licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution license (<http://creativecommons.org/licenses/by/3.0/>).